

Dalchem - TC78

Product Characteristics: TC78 is a low viscosity, rapid setting, two component rigid urethane compound.

Benefits: TC78 is rapid setting and demonstrates more flexibility than other similar materials. This urethane is compatible with a wide range of fillers and can reproduce intricate detail as a result of its low viscosity

Colour:	White
Specific Gravity:	1.05 gm/cc
Hardness:	78 Shore D
Pot Life:	5 min
Demould Time:	5-30 min
Application:	Optimum @ 25°C
Mix Ratio:	100:100 by wgt
Shelf life:	6 month from Date of Manufacture
Viscosity	60mpa.s
Heat Resistance	>85°C
Tensile Strength	40mpa
Flexural Modulus	67mpa





Applications: TC78 is recommended for applications where a "thermoplastic feel" is desired. It is commonly used to make computer housings, models of all kinds, artwork, and can also be used for electronic component encapsulation.

Dalchem offers no warranty of merchantability nor fitness for use, nor any other express or implied warranty. The users exclusive remedy and the suppliers sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind. Suggestions for use should not be taken as inducements to infringe any patents.
